

Bending of profiles coated with LG Hausys film

It is recommended that LG Hausys film- coated profiles be seasoned for at least 6 weeks before they are bent. The seasoning conditions:

- temperature 23-25°C
- humidity 30-40%.

In addition, strong sunlight should be avoided.

Distribution and warehouse in Poland:

eco in spółka z ograniczoną odpowiedzialnością sp. k.
ul. Powińska 18, 02-920 Warsaw
tel./fax 022 651 68 14
www.ecoin.pl, e-mail: biuro@ecoin.pl